



230 GSM



320 GSM

100% POLYESTER RIPSTOP, FLAME AND WATER RESISTANT

Specifications

Finished weight	230 gsm	320 gsm	
Grey Weight	190 gsm	250 gsm	
Tensile Strength (5X20 cm strip)	Warp	1700 N	2250 N
	Weft	1300 N	1460 N
Tear Strength (Tongue Tear)	Warp	86 N	105 N
	Weft	120 N	120 N
Pressure Head	55 cms	65 cms	
Cone Test Stands For	12 hours	18 hours	
Yarn Used	150 D	300 D	
After Flame/Glow	0/0	0/0	

- Light weight
- Wash Resistant
- Pigmented Colours Available
- Flouro Carbon Finished
- Durable Flame Resistant Finish